

ABSTRACT OF THE DISCLOSURE

On a Si substrate are formed successively a Ge interfacial layer as a dislocation controlling layer and a SiGe film. Then, at least at the region of the SiGe film near the Si substrate are formed 90 degrees dislocations.